


DuPont™ Riston® GoldMaster GM100 Series

DATA SHEET & PROCESSING INFORMATION

Photopolymer Dry Film for Nickel/Gold & Specialty Plating Applications



Product Features/ Applications

Riston® GoldMaster GM100 has very strong resistance to lifting on all surfaces. It has been formulated to be compatible with incoming copper clad surfaces, scrubbed and unscrubbed electroless, direct metalization processes and panel plated copper. Riston® GoldMaster GM100 is designed to be used in Nickel/Gold and specialized plating applications such as thick copper plating or selective Sn/Pb strip. The thicker versions (eg. 75 and 100µm) are suitable for conformation over circuitry as secondary plating resists.

Processing Data

This Processing guide documents specific process information for Riston® GoldMaster GM100. Data quoted in this guide have been generated using production equipment as well as laboratory test methods and are offered as a guideline. Actual production parameters will depend upon the equipment, chemistries, and process controls in use, and should be selected for best performance. For more background on general processing see the General Processing Guide.



The miracles of science™

PART 1: Copper Surfaces and Surface Preparation

Riston® GoldMaster GM100 has very strong resistance to lifting on all surfaces. Riston® GoldMaster GM100 is compatible with the following surfaces and surface preparations:

- Electroless:
 - Unscrubbed with/without antitarnish
 - Pumice and Brush scrubbed
- Direct metallization surfaces
- Panel plated copper
 - Unscrubbed with/without antitarnish
 - Scrubbed

Antitarnish

The following antitarnishes have been used successfully per manufacturers' processing recommendations:

- Duratech PCL
 - Enthone Entek Cu56
- (Others may give equally acceptable results)

For prelamination cleaning suggestions, see General Processing Guide and its references.

PART 2: Lamination

Lamination Conditions for DuPont HRL-24/Yieldmaster® Film Laminator

- Pre-Heat: Optional
- Lam. Roll Temp.: 110-120°C (230-245°F)
- Recommended: 115°C (239°F)

Note: Expected Board Exit Temperature: 50-55°C (120-130°F)

For information on how to use Board Exit Temperature for process control, see General Processing Guide.

- Roll Speed: 0.6-1.5 m/min (2-5 ft/min)
 - Air Assist Pressure: 0-2.8 bar (0-40 psig)
- Note: for ≥ 1.4 bar use heavy-duty rolls)

Lamination Conditions for Automatic Sheet Laminators

- Pre-heat: Optional
- Seal Bar Temp.: 50-80°C
- Lamination Roll Temp.: 100-115°C

Note: Expected Board Exit Temperature: 50-55°C (120-130°F)
(For information on how to use Board Exit Temperature for process control, see General Processing Guide)

- Seal Bar Pressure: 3.5-4.5 bar (50-65 psig)

- Lam. Roll Pressure: 3.0-5.0 bar (43-72 psig)
- Seal Time: 1-4 seconds
- Lamination Speed: 1.5-3 m/min (5-10 ft/min)

PART 3: Exposure

Riston® GoldMaster GM100 can be exposed on all standard equipment used in the printed circuit board industry. Choose lamps that compliment the peak resist response of 350 to 380 nm.

Riston® GoldMaster GM100 has better resolution and wider exposure latitude than other resists. It is also more resistant to off-contact exposure defects, which are common in glass/glass exposure frames.

Resolution down to 50 microns (2 mil) lines and spaces is possible with Riston® GoldMaster GM100 in optimized production environments.

| Recommended Exposure Range | | | |
|----------------------------|-------|-------|--------|
| | GM120 | GM130 | GM140 |
| Nominal Thickness | 50µm | 75µm | 100µm |
| RST 25 | 10-18 | 10-18 | 10-18 |
| SST 21 | 7-9 | 7-9 | 7-9 |
| SST 41 | 19-28 | 19-28 | 19-28 |
| mJ/cm ² | 30-75 | 40-95 | 55-110 |

Suggestions:

- Start with RST 13-14 for fine line applications, (100 microns L/S).
- Start with RST 15-16 for ≥ 125 microns L/S.

Note:

- RST = DuPont Riston® 25-Step Density Tablet (read as highest resist step)
- SST 41 = Stouffer 41-Step Sensitivity Guide (read as highest resist step)
- SST = Stouffer 21-Step Sensitivity Guide (read as highest resist step)
- Exposure energy (mJ/cm²) from International Light Radiometer model IL1400A with Super Slim UV Probe (SSL001A) on an Olec AP30-8000 exposure unit.

PART 4: Development

Riston® GoldMaster GM100 can be developed in sodium or potassium carbonate with good productivity. It has wide development latitude.

Development Recommendations

- **Spray Pressure:** 1.4-2.2 bar (25-30 psig)
High impact direct-fan or cone nozzles preferred
- **Chemistry:**
 - Na₂CO₃ 0.7-1.0 wt%; 0.85 wt% preferred
 - Na₂CO₃·H₂O 0.8-1.1 wt%; 1.0 wt% preferred
 - K₂CO₃ 0.75-1.0 wt%; 0.9 wt% preferred

Note: The use of buffered development solutions, containing KOH (Potassium Hydroxide) or NaOH (Sodium Hydroxide), is not recommended with DuPont Riston® Photoresists. These solutions can lead to excessive foaming and high dissolved photoresist loading, compromising sidewall quality and photoresist resolution. Also, use of buffered chemistries can increase residue build-up in the developer, resulting in increased weekly equipment clean-out costs.

- **Temperature:** 7-35°C (80-95°F); 30°C (85°F) preferred
- **Breakpoint:** 50-65% (60% preferred)
- **Dwell Times (approx.):**
 Riston® GM120: 32-42 secs
 Riston® GM130: 48-63 secs
 Riston® GM140: 64-84 secs
- **Resist Loading:**
 Feed & Bleed 4-8 mil-ft²/gal; 0.07-0.14 m²/liter
 Batch To 12 mil-ft²/gal; to 0.20 m²/liter
- **Rinse Water:** Hard water (150-250 ppm CaCO₃ equivalent), or soft water are acceptable
- **Rinse Spray Nozzles:** High Impact, direct fan nozzles preferred
- **Drying:** Blow dry throughly; Hot air preferred

Note:

Dwell Time ranges were established in Chemcut 547 type developer equipment, using sodium carbonate and 2-10 mil-ft²/gal (0.07-0.17 m²/liter) loading, with all other variables set within the preferred ranges mentioned above.

Defoamers

Riston® GoldMaster GM100 could require the use of a defoamer. If required, add 0.8 ml/liter (3 ml/gallon) of one of these antifoams:

Pluronic 31R1; Dexter DF1205; RBP BB
 Others may work equally well.

**PART 5: Plating
 (acid copper sulfate; tin/lead; tin;
 nickel; gold)**

(Follow plating vendors' recommendations)
 Riston® GoldMaster GM100 can be used for pattern plate processes with acid copper, tin/lead, tin, nickel and gold plating baths. Riston® GoldMaster GM100 has very strong resistance to lifting and underplating. The standard plating process conditions should not be altered for the GoldMaster GM100 test probe.

Recommendations: Preplate Cleaning Process Sequence

- Acid Cleaner : 38-50°C (100-120°F); 2-4 minutes
- Spray Rinse: 2 minutes
- Microetch to remove 0.15-0.25 µm (5-10µ") copper (time: as required)
- Spray Rinse: 2 minutes
- Sulfuric acid (5-10 vol%) dip; 1-2 minutes
- (Optional: spray rinse; 1-2 minutes)

PART 6: Etching

- The chemical resistance of GoldMaster GM100 makes it compatible with most commonly used etchants in the PCB industry (eg. ammonical etch and acid etchants cupric chloride, H₂O₂/H₂SO₄, ferric chloride).

PART 7: Stripping

Riston® GoldMaster GM100 is formulated to dissolve slowly in stripping solution after breaking up into pieces. This can greatly increase the life of the stripping solution and reduce costs, if the resist can be removed before dissolving. Filtration is strongly recommended.

Stripping Recommendations

- **Chemistry:**
 NaOH: 1.5-3 wt%; faster stripping at 3 wt%
 KOH: 1.5-3 wt%; faster stripping at 3 wt%
 Proprietary Strippers: Concentration per vendor recommendation
 Spray Pressures: 1.4-2.4 bar (20-35 psig)
 Spray Nozzles: High impact direct fan
 Breakpoint: 50% or lower

- **Stripper Dwell Times** (seconds) at 55°C (130°F). Dwell time is the total time spent in the stripper, given a 50% breakpoint:

Defoamers:

| Chemistry | GM120 | GM130 | GM140 |
|--------------|---------|---------|---------|
| 3.0 wt% NaOH | 90-120 | 120-160 | 150-200 |
| 1.5 wt% NaOH | 150-180 | 190-240 | 250-300 |
| 3.0 wt% KOH | 90-120 | 120-160 | 150-200 |
| 1.5 wt% KOH | 150-180 | 190-240 | 250-300 |

Follow recommendations in Development Section.

Proprietary Strippers:

The following proprietary strippers have been used successfully for GoldMaster GM100.

RBP ADF-30; Dexter RS1624; NTS402HV

Others may perform equally well.

Generic mixtures of 3% NaOH (or KOH) plus 3% MEA (monoethanolamine) have also been used successfully.

For further information, please contact your local representative.

DuPont Electronic Technologies
14 T. W. Alexander Drive
Research Triangle Park, NC 27709 USA

www.imaging-materials.dupont.com

This information corresponds to DuPont's current knowledge on the subject. It is offered solely to provide possible suggestions for your own experiments and is not intended to substitute for any testing you may need to conduct to determine the suitability of DuPont's products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available.

Since DuPont cannot anticipate all variations in actual end-use conditions, it makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right

Caution : Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement", H-51459.



The miracles of science™